

4Ever Concrete Floor FOP

Primer-less high performance nano epoxy floor coating

Characteristics

4Ever Concrete floor FOP is 2 component epoxy-based floor coating for use on the oily floor in industrial maintenance environments and high performance architectural applications with nano technology.

- Strong adhesion on the oily concrete floor
- Simpler to use in one layer. No need for primer
- Quick drying time. 6hrs
- Excellent anti fouling for tire skid mark
- Easy to repair. Saves time and cost.

Product data

Color

Standard 10 colors: Green, Light green, Grey, Light grey, Skyblue, Orange, Yellow, Ivory, Brown, White

Packaging

10kg sets(Part A:5kg, Part B: 5kg)

Shelf life/Storage

12months(Protect from direct sunlight. if stored properly in original, unopened and undamaged sealed packaging.)

Technical data

COVERAGE	285-350 g/m ² (depending on concrete)
FILM THICKNESS	170 -190 µm
APPLICATION	Roller, brush
POT LIFE	30-40mins(20°C, 60% humidity)
DRY TO TOUCH	2 - 3 hours (20°C, 60% humidity)
FULL CURE	6 hours (20°C, 60% humidity)
For HEAVY TRAFFIC	24hours(20°C, 60% humidity)

TEST	DESCRIPTION	RESULT
ADHESION	Pulloff test	7.1 N/mm ²
ADHESION	JIS K 5600-5-6 Cross Cut	No delamination
SCRATCH	JIS K 5600-5-4 Scratch hardness (Pencil method)	3H
IMPACT RESISTANCE	JIS K 5600-5-3 Dropping 500g steel ball from 50cm(Falling-weight test by Dupon method)	No damage
HEAT RESISTANCE	JIS K 5600-6-3 The effect of heat	150°C
ABRASION RESISTANCE	JIS K 5600-5-9 Rotating abrasive rubber wheel method	100 mg
CHEMICAL RESISTANCE	Resistance to many chemicals. Please ask for detailed information.	

Application procedures

Surface preparation

- Concrete needs 30days of air drying for concrete curing period.
- ※ For the surface that does not meet above requirements, coating has to be waited until standard developing period elapsed
- Confirm that concrete surface is smooth. If lack of smoothness exceeds 200µm, then make the surface smooth by sanding or grinding.
- The concrete substrate must be sound and of sufficient compressive strength with a minimum pull-off strength of 1.5N/mm².
- All contaminants such as dust, loose, oil and friable material must be completely removed from all surfaces before application of the product, preferably by brush and/or vacuum.
- Be sure that moisture content ratio is less than 10%.

Mixing time

- Stir Part A with an electric mixer thoroughly for at least 1 minute until color is uniformed.
- Stir Part B with an electric mixer thoroughly for at least 1 minute until color is uniformed.
- Mix Part A and Part B on 1:1 ratio by weight. Then, mix thoroughly with an electric mixer for at 3 minutes until color is uniformed.

Applying paint

- Remove any excess fur from the roller using duct tape.
- Use small brush (15 or 30 mm) to paint edges on the area.
- Use spatula to fill up the crack area. Remove excess paint by levelling it using spatula and wait for the paint to seep inside the crack. Once the paint has seeped in, re-fill the crack again until slightly overflowing.
- Use roller for large flat area. (Roller size: 6 or 9 inch)
- Apply paint vertically (130~150g/m²)
- When you can walk on the first coating film, start second coating. (allow to dry for about 2-3 hours after first coating)
- After painting vertically, continue to paint horizontally and softly. (155~200g/m²)
- After finishing painting, soak all the brushes in container which contains respective Reducer.
- Cover the surface of the solvent container with tape, to avoid evaporation.
- After finishing painting, keep remaining paint in can properly.
- Remove tape and clean any spillage on the mouth of the paint can with EP Reducer.
- Use scraper and hammer to tighten the lid.

Caution

- At temperature of 30-35°C, the paint should be applied within 20 mins. For your reference, proper paint amount is 2kg per 1 person for 20 mins.
- When used outdoor or exposed to the sun, this may cause yellowing, fading or chalking.
- When temperature is low, condensation on the painting during curing may cause blushing.
- This product is designed for many kinds of oil, except for silicone oil and fish oil.

Disclaimer

The information in this document is given to the best of Somay Q's knowledge, based on laboratory testing and practical experience and is for guidance only. All recommendations relating to the use of Somay Q products is dependable and to its best knowledge. Somay Q's products are considered tools for skilled applicators with prerequisite knowledge. Somay Q cannot be held responsible for surface and substrate preparation which is beyond Somay Q's control. Somay Q can only guarantee the quality of the product. Minor product variations may be implemented in order to comply with local requirements. Somay Q reserves the right to change the given the date and application instructions and methods without further notice. Somay Q should be consulted on specific problems and the general suitability of this product for end users specific requirements and specific application practices.